


# PRODUCT SUBMITTAL - LADDER EYE

Ladder Eye Joint reinforcing is designed for embedment in the horiziontal mortar joints of concrete masonry units.



# **Recycled Content:**

85% Post-Consumer 10% Post-Industrial

# **Material Conformance**

Ladder Eye Joint reinforcing is designed for embedment in the horiziontal mortar joints of concrete masonry units.

ASTM A951/A951M (Standard Specification for Steel Wire for Masonry Joint Reinforcing.)

Meets TMS 402/602 & ACI / ASCE 530 Building Code Requirements and Specification for Masonry Structures

Wire: (Carbon Steel) ASTM A1064 / A1064M

Tensile Strength: 80,000 psi. - Yield Point 70,000 psi.

Mill Galvanized ASTM A641 / ASTM A641M (0.1 oz/ft)

Hot Dip Galvanized after fabrication.


ASTM A153 / ASTM A153-B2 (1.5 oz/ft)

# **Product Details**

Cross rods welded 16" o.c.

10 ft long pieces

Wire deformations meet ASTM A951



#### Structural Performance:

Capable of withstanding 100 lbs load in tension and compression without deforming or developing play in excess of .05 inch. (Test results available upon request)

Eye wire weld height will not exceed half the dimension of the mortar joint (3/8" joint = 3/16" max reinforcement). This meets TMS 402/602 Building Code Requirements and Specification for Masonry Structures.

FIIII3II		
Hot Dip Galvanized		
Wire Diameter:	Side Rods	Cross Rods
Standard	9 Gauge (.148")	9 Gauge (.148")
CMU / Block Size:		
4" 6" 8" 10"	12"	
Insulation Thickness:		
0"	2 1/2" 3"	3 1/2" 4" [
3/16" Diameter Hook (Pintle) Length:		

RESET EMAIL PRINT

### NOTE

The information contained on this submittal sheet does not constitute any professional opinion or judgement and should not be used as a substitute for any architect or engineer professional determinations. Each construction project is unique and the use of these products is the responsibility of the architects, engineers and other professionals who are familiar with the specific design of the project.